



## Prep™ 125 Concentrated Degreaser

A highly concentrated degreaser designed for removing heavy oil and grease contamination from floors, equipment and machinery.

### Features and Benefits

- Safe on aluminum, magnesium, cad plate, and other structural metals
- Safe on paint and Plexiglas™
- Can be sprayed, brushed, mopped, or dipped
- Water-based, co-solvent formulation
- Non-flammable, biodegradable
- Contains No TAP's or HAP's (Toxic/Hazardous Air Pollutants)
- No DOT shipping restrictions

### Recommended Use

- Transportation vehicles
- Equipment, machinery, engine parts
- Wheels, wheel wells, rims, barbecues
- Factory and warehouse floors
- Garage and concrete floors
- Removing chewing gum

### Product Data

Appearance:	Translucent orange liquid
Specific Gravity:	1.0
Boiling Point:	212°F (100°C)
Freezing Point:	32°F (0°C)
pH:	11.5 (concentrate)
Flash Point:	221°F (105°C)
Coverage:	50 to 500 sq. ft/gal (Theoretical)
VOC (Concentrate):	< 10g/L
Shelf Life:	24 months

### Safety Precautions

Proper safety procedures should be followed at all times while handling this product. Refer to the Material Safety Data Sheet for important health/safety information before use. **For Professional Use Only; Not Intended for Household Use.**

MSDS are available through the DuraPrep® website, [www.ppg.com/surfaceprep](http://www.ppg.com/surfaceprep) or by calling 412-434-4515.

### Packaging

1 gal (3.8 L)	
5 gal (19.0L)	
55 gal (210 L)	Special Order
330 gal (1254 L)	Special Order

### Limitations of Use

Surface temperatures should be between 32°F to 120°F (0°F and 49°C).



## Directions for Use:

### Typical Dilution Ratios:

- Light Duty Cleaning  
1 part **Prep™125**: 9 parts water
- Medium Duty (Routine) Cleaning  
1 part **Prep™125**: 4 parts water
- Heavy Duty Cleaning  
1 part **Prep™125**: 1 parts water

**Test Area:** Always prepare a test area to determine product performance, coverage and applicable dilution ratios, as well as the suitability of product for the paint and the substrate.

**Mixing:** After appropriate dilution is determined by test patch, add the proper amount of **Prep™125** to water and agitate.

**Application and Removal:** Apply properly diluted **Prep™125** with mop, brush, or spray. Allow to remain on surface for up to 30 minutes, agitate the surface with a brush, and rinse with water. For best results, use a pressure washer.

**Re-Coating:** After sufficient drying time, ensure the surface is dry and dust-free prior to recoating in accordance with good painting practice and the coating manufacturer's instructions.

---

PPG believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.



PPG Industries, Inc.  
Surface Solutions  
One PPG Place  
Pittsburgh, PA 15272  
[www.ppg.com/surfaceprep](http://www.ppg.com/surfaceprep)