



Prep™ 130 Industrial Cleaner (Gel)

A gelled, ready-to-use, product that can be sprayed, brushed, rolled or mopped on and cling to the surface to provide extended dwell time in hard to reach areas. Designed for large structures, vertical surfaces, and other areas where increased contact time may be substituted for scrubbing.

Features and Benefits

- Viscous liquid that clings to vertical surfaces
- Brush, roll, mop or spray application
- Safe on paint and Plexiglas™
- Safe on aluminum, magnesium, cad plate, and other structural metals
- Water-based (non-petroleum)
- Non-flammable, biodegradable
- Contains No TAP's or HAP's (Toxic/Hazardous Air Pollutants)
- No DOT shipping restrictions

Recommended Use

- Areas where increased contact time may substitute for scrubbing
- Painted and unpainted surfaces
- Carbon and soot removal
- Equipment and machinery
- Engine parts
- Wheels, wheel wells, rims, barbecues

Product Data

Appearance:	Translucent orange gel
Specific Gravity:	1.0
Boiling Point:	212°F (100°C)
Freezing Point:	32°F (0°C)
pH:	11.5 (concentrate)
Flash Point:	N/A
Coverage:	50 to 500 sq. ft/gal (Theoretical)
VOC (Concentrate):	36 g/L
Shelf Life:	24 months

Safety Precautions

Proper safety procedures should be followed at all times while handling this product. Refer to the Material Safety Data Sheet for important health/safety information before use. **For Professional Use Only; Not Intended for Household Use.**

MSDS are available through the DuraPrep® website, www.ppg.com/surfaceprep or by calling 412-434-4515.

Packaging

1 gal (3.8 L)	
5 gal (19.0L)	
55 gal (210 L)	Special Order
330 gal (1254 L)	Special Order

Limitations of Use

Surface temperatures should be between 32°F to 120°F (0°C and 49°C).



Directions for Use:

Test Area: Always prepare a test area to determine product performance, coverage and applicable dilution ratios, as well as the suitability of product for the paint and the substrate.

Prep™130 is typically used full strength with 30 minute contact time for hard-to-reach areas or to reduce or substitute for scrubbing.

Mixing: if dilution is needed, add the proper amount of **Prep™130** to water and agitate.

Typical Dilution Ratios:

- Light Duty Cleaning
1 part **Prep™130**: 9 parts water
- Medium Duty (Routine) Cleaning
1 part **Prep™130**: 4 parts water
- Heavy Duty Cleaning
1 part **Prep™130**: 1 parts water

Dwell Time: Allow product to dwell from 2 to 30 minutes, depending on amount of soiling and ability to agitate.

Application & Removal: Apply properly diluted **Prep™130** with mop, brush, roller or sprayer. Allow to remain on surface for up to 30 minutes, agitate the surface with a brush, and rinse with water. For best results, use a pressure washer.

Coating: After sufficient drying time, ensure the surface is dry and dust-free prior to coating in accordance with good painting practice and the coating manufacturer's instructions.

PPG believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.



PPG Industries, Inc.
Surface Solutions
One PPG Place
Pittsburgh, PA 15272
www.ppg.com/surfaceprep